



PRODUCT SPECIFICATIONS

PRODUCT

SKU/Color Names :

| | |
|------------------------------|-----------------------------|
| PANZU-101 Zion | PANZU-107 Cascades |
| PANZU-102 Acadia | PANZU-108 Big Bend |
| PANZU-103 Teton | PANZU-109 Sequoia |
| PANZU-104 Mesa Verde | PANZU-110 Bryce |
| PANZU-105 Glacier Bay | PANZU-111 Pinnacles |
| PANZU-106 Carlsbad | PANZU-112 Shenandoah |

Construction :

- 3.5mm Rigid Core (Stone and Virgin DOTP Composite)
- 1.2mm IXPE attached cushion (No VOCs)
- 5 unique planks per pattern, 10 with a flip

Wear Layer :

12mil with Quantum X™ Technology Finish (Proposition 65 Compliant)

Installation :

- Click, Valinge Locking System
- Float or Glue Down
- 50 LF before transition needed
- Matching Accessories: 3-in-1 Molding, Flush Stair Nose
- Use Polyurethane for wet spaces. Pressure sensitive adhesive is acceptable for other spaces. Please reference our installation instructions for further details or contact sales@duratousa.com

*A 50'x50' install requires 10mm expansion space along walls in uncontrolled environments (such as no HVAC).

*Do not install below 50°F, 24-hr acclimation time.

*Use a floor mat for office chairs.

SIZE/PACKAGING

Plank Size : 7" x 48"

Planks/Carton : 12 Sq. Ft./Carton : 28.365

Cartons/Pallet : 50 Sq. Ft./Pallet : 1,418.25

Sq. Ft./Container : 28,365


FEATURES



TEST DATA

| | |
|--|---|
| ASTM E492-09 Impact Sound Conduction & ASTM E90-09 Airborne Sound Conduction | 6" slab, no drop ceiling: STC 52 db / IIC 54 db / HIIC 60 db OSB subfloor with fiberglass and open truss using standard resilient channel with fastened gypsum board: STC 59 db / IIC 50 db / HIIC 61 db |
| ASTM D2394 Slip Resistance DCOF (Sliding) | Dry: 0.67 Wet: 0.50 |
| ASTM D1037 Dynamic Load Limit | 1,162 psi |
| ASTM F970-22 Static Load Limit | Passes, 0.29mm indent, 250 psi |
| ASTM F1914-18 Residual Indentation | Meets or Exceeds, average 0.05mm |
| ASTM F2199-20 Dimensional Stability | Meets or Exceeds |
| ASTM E648 Critical Radiant Flux | Meets or Exceeds, Class 1 (>1.10) |
| ASTM F1514-19 Resistance to Heat | Meets or Exceeds, average ΔE^* 0.26 |
| ASTM F1515-21 Resistance to Light | Meets or Exceeds, average ΔE^* 0.74 |
| ASTM F925-13 Resistance to Chemicals | No change, Not affected |
| ASTM E662 Smoke Density | Meets or Exceeds, <400 |


WARRANTY



HEADQUARTERS
600 Edwards Road
Fort Pierce, FL 34982
ph: 267.343.3480

DURATO PHILLY
9800 Bustleton Avenue
Philadelphia, PA 19115

DURATO HOUSTON
8451 Market Street,
Suite 150
Houston, TX 77029



duratocontract.com